



PE120

POLYESTER WEB ADHESIVE

KEY FEATURES

- Moderate heat activation temperature
- Excellent adhesion to textiles and urethane foam
- Good temperature resistance



AUTOMOTIVE UPHOLSTERY

INDUSTRIAL FILTER MEDIA

DECORATIVE FABRIC CONSTRUCTIONS

TYPICAL PHYSICAL PROPERTIES

Description	Results
Appearance	Milky White
Basis Weight Range	15-100 g/yd ² (18-120 g/m ²)
Trimmed Width	10 to 68 in (25 to 173 cm)
Melt Point	120°C
Min. Activation Temp.	138°C

BOSTIK HOTLINE

Smart help
1-800-726-7845

Bostik, Inc.
11320 W. Watertown Plank Road
Wauwatosa, WI 53226
www.bostik-us.com



This document supersedes all previously published literature.
06.21.2018